

ZISAMIDE®

POLYAMIDE 6

Properties	Unit	TP4204	TP4208	TP4209	TP4214	TP4407	TP6603	TP6605	TP6802	SP4212
含水量 Moisture content	ppm	< 1000	< 1000	< 1000	< 1000	< 1000	< 1000	< 1000	< 1000	< 1000
可萃取物 Extractable	%	< 0.6	< 0.6	< 0.6	< 0.6	< 0.6	< 0.6	< 0.6	< 0.6	< 0.6
密度 Density	g/cm ³	1.12 ~ 1.15	1.12 ~ 1.15	1.12 ~ 1.15	1.12 ~ 1.15	1.12 ~ 1.15	1.12 ~ 1.15	1.12 ~ 1.15	1.12 ~ 1.15	1.12 ~ 1.15
容積密度 Bulk density	kg/m ³	ca. 650	ca. 650	ca. 650	ca. 650	ca. 650	ca. 650	ca. 650	ca. 650	ca. 650
熔點 Melting point	°C	220	220	220	220	220	220	220	220	220
熔融指數 MVR	cm ³ /10min	85 ~ 105 (235°C / 5.0kg)	70 ~ 90 (235°C / 5.0kg)	40 ~ 80 (235°C / 5.0kg)	290 ~ 350 (235°C / 5.0kg)	30 ~ 70 (235°C / 5.0kg)	20 ~ 60 (275°C / 5.0kg)	50 ~ 90 (275°C / 5.0kg)	10 ~ 30 (275°C / 5.0kg)	80 ~ 110 (235°C / 5.0kg)

Packaging: 800 kgs Jumbo Bag <16mt / 20' Container>

25 kgs Paper Bag <15mt / 20' Container>

2020