

ZISAMIDE®

POLYAMIDE 6

Properties	Unit	HP1101	HP2201	HP3207	HP3402
相對黏度 Relative viscosity	-	2.47±0.03	2.47±0.03	2.47±0.03	2.80±0.03
含水量 Moisture content	ppm	< 600	< 600	< 600	< 600
胺基 Amino end group	meq/kg	44±3	44±3	44±3	41±3
可萃取物 Extractable	%	< 0.6	< 0.6	< 0.6	< 0.6
二氧化鈦 TiO ₂	%	0.3±0.02	1.60±0.10	-	-
熔點 Melting point	°C	220	220	220	220

Packaging: 800 kgs Jumbo Bag <16mt / 20' Container>
25 kgs Small Bag <15mt / 20' Container>

2021