

# ZISAMIDE®

## POLYAMIDE 6

Properties	Unit	TP4208	TP4407	TP6603
相對黏度 Relative viscosity	-	2.45±0.05	2.70±0.05	3.35±0.10
含水量 Moisture content	ppm	< 1000	< 1000	< 1000
可萃取物 Extractable	%	< 0.6	< 0.6	< 0.6
胺基 Amino end group	meq/kg	44±3	51±3	39±3
密度 Density	g/cm <sup>3</sup>	1.12 ~ 1.15	1.12 ~ 1.15	1.12 ~ 1.15
容積密度 Bulk density	kg/m <sup>3</sup>	ca. 650	ca. 650	ca. 650
熔點 Melting point	°C	220	220	220
熔融指數 MVR	cm <sup>3</sup> /10min	70 ~ 90 (235°C / 5.0kg)	30 ~ 70 (235°C / 5.0kg)	20 ~ 60 (235°C / 5.0kg)

Packaging: 800 kgs Jumbo Bag <16mt / 20' Container>

25 kgs Small Bag <15mt / 20' Container>

2021